

### Permeation breakthrough times according to EN 16523-1:2015

CHEMICAL AGENT	CAS NUMBER	MEAN BREAKTHROUGH TIME (MINUTES)	PROTECTIVE INDEX	PART
Sodium Hydroxide NaOH 40%	1310-73-2	>480	6	Palm
Ammonia 25%	7664-41-7	8	0	Palm
Formaldehyde 37%	50-00-0	>480	6	Palm
Isopropyl alcohol (IPA) 70%	67-63-0	9	1	Palm
Ethanol 70%	64-17-5	10	0	Palm

### Historical permeation data according to EN 374-3:2003

CHEMICAL AGENT	CAS NUMBER	MEAN BREAKTHROUGH TIME (MINUTES)	PROTECTIVE INDEX	PART
Formaldehyde 30%	50-00-0	>480	6	Palm
Hydrochloric Acid 32%	7647-01-0	448	5	Palm
Sodium Hypochlorite 12%	7681-52-9	>480	6	Palm

RATING SYSTEM						
0	1	2	3	4	5	6
<10	10-30	30-60	60-120	120-240	240-480	>480
<b>NOT RECOMMENDED</b>	<b>SPLASH PROTECTION</b>		<b>MEDIUM PROTECTION</b>		<b>HIGH PROTECTION</b>	

Data given in the table above are based on results of laboratory tests performed on the palm area of the glove or on the cuff area if relevant. These tests were run using standard test methods that may not adequately replicate any specific conditions of end use. We wish to highlight that permeation times do not equate to safe wear time. Because Ansell has no detailed knowledge or control over the conditions of end use, any of these data must be advisory only, and Ansell must decline any liability.

### Contact your Ansell representative for ordering or more information.

#### North America

US Tel: 800 952 9916  
CA Tel: 1-844-494-7854  
Email: insidesalesus@ansell.com

#### Central & South America

Tel: +52(442) 296 20 50  
Email: cslac@ansell.com

#### Brazil

Tel: +55-11-3356-3100  
Email: luvas.medicas@ansell.com

#### Europe, Middle East & Africa

Tel: +32 (0) 2 528 74 00  
Email: info@ansell.eu

#### Asia Pacific

Tel: +603 8310 6688  
Email: apac.medical@ansell.com

#### Australia & New Zealand

Tel: +61 3 9270 7270  
Email: protection@ap.ansell.com